

SHIVACHLOR 0011

SHIVACHLOR 0011 is a chlorinated paraffin based on a (C10-C13) paraffin and is ROHS compliant. It is a versatile and low colour grade used in a number of industries and applications ranging from use as a secondary plasticiser and flame retardant additive in PVC to use in paints, sealants and adhesives.

Further information may be obtained from the website 'www.shiva-group.com/www.shivtekspechemi.com'. **SHIVACHLOR 0011** is not classified as hazardous for transport or use and is available in HmHDPE/STEEL drums of 220-275 kgs nett weight as well as in IBC (1200 kg- 1300 kg) or in flexi Bags/Bulk Isotainers.

TECHNICAL DATA SHEET OF SHIVACHLOR 0011 CP PLASTICISER

SP.GVT @ 27 DEGREES CELCIUS	1150-1170
COLOUR HAZEN (Hu)	20-30
CHLORINE CONTENT (%W/W)	39-42%
VISCOSITY (27 DEG) POISE (BROOKFIELD)	60-120
FREE MINERAL ACIDITY	5-7
FREE CHLORINE	0.00010
VOLATILE LOSS (130 DEG/3 HRS) %	1.0 MAX
HEAT STABILITY (180 DEG/30 MIN)	LIGHT YELLOW
PH VALUE	6.0
REFRACTIVE INDEX (@ 27 DEG)	1.450

For further information, please contact:
 "SHIVTEK SPECHEMI INDUSTRIES LTD"
 1419, Tower-1, DLF Corporate Green, Sector-74 A SPR Road,
 Gurugram, Haryana-122004 (INDIA)
 Phone no: 0124-6904448

www.shiva-group.com

Information in this publication is believed to be accurate and is given in good faith, but it is for the customer to satisfy itself of the suitability for its own particular purpose. Accordingly, Shiva Group gives no warranty as to the fitness of the product for any particular purpose and any implied warranty or condition (statutory or otherwise) is excluded except to the extent that such exclusion is prevented by law. Freedom under Patent, Copyright and Designs cannot be assumed.

Disclaimer:-

Color indicated are with Optical Brightener (OB+) only. Without OB+ color increases by 40-50 Hu.

Viscosity measured is on specific batch made from specific paraffin range. The viscosity can change from $\pm$ 5-7 poise depending upon incoming raw material range.

TDS prepared is on specific batch of specific paraffin range only. Some minor range bound differences may appear from batch to batch due to change in paraffin range.

Samples kept for 12 hours at a specified temperature before conducting test.

The specifications are solely checked by SHIVA in house Laboratory and are indicative. All specs needs to be cross examined before confirming commercial deals.

This document cannot be used for any legal purpose.

Revised Date: 05-Feb-25

Shivtek Spechemi Industries Ltd

(Formerly known as Shhivtek Industries Private Limited)

CIN No. U24100DL2009PLC188730

- 1419, DLF Corporate Green Tower 1, Sector 74 A, Southern Peripheral Road (SPR), Gurugram, Haryana-122004 (India).
- +91-124-6904448 • info@shivtekspechemi.com, sales@shivtekspechemi.com
- www.shivtekspechemi.com, www.shiva-group.com



SHIVACHLOR – 2211

SHIVACHLOR – 2211 is a chlorinated paraffin based on a (C10-C13) paraffin and is ROHS compliant. It is a versatile and low colour grade used in a number of industries and applications ranging from use as a secondary plasticiser and flame retardant additive in PVC to use in paints, sealants and adhesives.

Further information may be obtained from the website 'www.shiva-group.com/www.shivtekspechemi.com'.

'SHIVACHLOR – 2211' is not classified as hazardous for transport or use and is available in HMHDPE/STEEL drums of 220-275 kgs nett weight as well as in IBC (1200 kg- 1300 kg) or in flexi Bags/Bulk Isotaines

TECHNICAL DATA SHEET OF SHIVACHLOR – 1950 CP PLASTICISER

SP.GVT @ 27 DEGREES CELCIUS	1150-1170
COLOUR HAZEN (Hu)	20-30
CHLORINE CONTENT (%W/W)	39-42%
VISCOSITY (27 DEG) POISE (BROOKFIELD)	5-7
FREE MINERAL ACIDITY	0.00010
FREE CHLORINE	NIL
VOLATILE LOSS (130 DEG/3 HRS) %	0.10 MAX
HEAT STABILITY (180 DEG/30 MIN)	LIGHT YELLOW
PH VALUE	6.0
REFRACTIVE INDEX (@ 27 DEG)	1.450

For further information, please contact:

"SHIVTEK SPECHEMI INDUSTRIES LTD"

1419, Tower-1, DLF Corporate Green, Sector-74 A SPR Road,

Gurugram, Haryana-122004 (INDIA)

Phone no: 0124-6904448

www.shiva-group.com

Information in this publication is believed to be accurate and is given in good faith, but it is for the customer to satisfy itself of the suitability for its own particular purpose. Accordingly, Shiva Group gives no warranty as to the fitness of the product for any particular purpose and any implied warranty or condition (statutory or otherwise) is excluded except to the extent that such exclusion is prevented by law. Freedom under Patent, Copyright and Designs cannot be assumed.

Disclaimer:-

Color indicated are with Optical Brightener (OB+) only. Without OB+ color increases by 40-50 Hu.

Viscosity measured is on specific batch made from specific paraffin range. The viscosity can change from $\pm$ 5-7 poise depending upon incoming raw material range.

TDS prepared is on specific batch of specific paraffin range only. Some minor range bound differences may appear from batch to batch due to change in paraffin range.

Samples kept for 12 hours at a specified temperature before conducting test.

The specifications are solely checked by SHIVA in house Laboratory and are indicative. All specs needs to be cross examined before confirming commercial deals.

This document cannot be used for any legal purpose.

Revised Date: 05- Feb-25

Shivtek Spechemi Industries Ltd

(Formerly known as Shivtek Industries Private Limited)

CIN No. U24100DL2009PLC188730

1419, DLF Corporate Green Tower 1, Sector 74 A, Southern Peripheral Road (SPR), Gurugram, Haryana-122004 (India).

+91-124-6904448 info@shivtekspechemi.com, sales@shivtekspechemi.com

www.shivtekspechemi.com, www.shiva-group.com



SHIVACHLOR – 2222

SHIVACHLOR – 2222 is a chlorinated paraffin based on a (C10-C13) paraffin and is ROHS compliant. It is a versatile and low colour grade used in a number of industries and applications ranging from use as a secondary plasticiser and flame retardant additive in PVC to use in paints, sealants and adhesives.

Further information may be obtained from the website 'www.shiva-group.com/www.shivtekspechemi.com'.

'SHIVACHLOR – 2222' is not classified as hazardous for transport or use and is available in HmHDPE/STEEL drums of 220-275 kgs nett weight or in bulk isotainers.

TECHNICAL DATA SHEET OF SHIVACHLOR – 2222 CP PLASTICISER

SP.GVT @ 27 DEGREES CELCIUS	1300
COLOUR HAZEN (Hu)	20
CHLORINE CONTENT (%W/W)	52-53%
VISCOSITY (27 DEG) POISE (BROOKFIELD)	2-4
FREE MINERAL ACIDITY	0.00010
FREE CHLORINE	NIL
VOLATILE LOSS (130 DEG/3 HRS) %	0.3 MAX
HEAT STABILITY (180 DEG/30 MIN)	LIGHT YELLOW
PH VALUE	6.0
REFRACTIVE INDEX (@ 27 DEG)	1.590

For further information, please contact:

"SHIVTEK SPECHEMI INDUSTRIES LTD"

1419, Tower-1, DLF Corporate Green, Sector-74 A SPR Road,
Gurugram, Haryana-122004 (INDIA)

Phone no: 0124-6904448

www.shiva-group.com

Information in this publication is believed to be accurate and is given in good faith, but it is for the customer to satisfy itself of the suitability for its own particular purpose. Accordingly, Shiva Group gives no warranty as to the fitness of the product for any particular purpose and any implied warranty or condition (statutory or otherwise) is excluded except to the extent that such exclusion is prevented by law. Freedom under Patent, Copyright and Designs cannot be assumed.

Disclaimer:-

Color indicated are with Optical Brightener (OB+) only. Without OB+ color increases by 40-50 Hu.

Viscosity measured is on specific batch made from specific paraffin range. The viscosity can change from $\pm$ 5-7 poise depending upon incoming raw material range.

TDS prepared is on specific batch of specific paraffin range only. Some minor range bound differences may appear from batch to batch due to change in paraffin range.

Samples kept for 12 hours at a specified temperature before conducting test.

The specifications are solely checked by SHIVA in house Laboratory and are indicative. All specs needs to be cross examined before confirming commercial deals.

This document cannot be used for any legal purpose.

Revised Date: 05- Feb-25

Shivtek Spechemi Industries Ltd

(Formerly known as Shihivtek Industries Private Limited)

CIN No. U24100DL2009PLC188730

1419, DLF Corporate Green Tower 1, Sector 74 A, Southern Peripheral Road (SPR),
Gurugram, Haryana-122004 (India).

+91-124-6904448 • info@shivtekspechemi.com, sales@shivtekspechemi.com

• www.shivtekspechemi.com, www.shiva-group.com



SHIVACHLOR – 1700

SHIVACHLOR – 1700 is a chlorinated paraffin based on a (C10-C13) paraffin and is ROHS compliant. It is a versatile and low colour grade used in a number of industries and applications ranging from use as a secondary plasticiser and flame retardant additive in PVC to use in paints, sealants and adhesives.

Further information may be obtained from the website 'www.shiva-group.com/www.shivtekspechemi.com'.

'SHIVACHLOR – 1700' is not classified as hazardous for transport or use and is available in HmHDPE/STEEL drums of 220-275 kgs nett weight as well as in IBC (1200 kg- 1300 kg) or in flexi Bags/Bulk Isotaines

TECHNICAL DATA SHEET OF SHIVACHLOR – 1700 CP PLASTICISER

SP.GVT @ 27 DEGREES CELCIUS	1350-1360
COLOUR HAZEN (Hu)	35-50
CHLORINE CONTENT (%W/W)	57-58%
VISCOSITY (27 DEG) POISE (BROOKFIELD)	5-12
FREE MINERAL ACIDITY	0.00010
FREE CHLORINE	NIL
VOLATILE LOSS (130 DEG/3 HRS) %	0.3 MAX
HEAT STABILITY (180 DEG/30 MIN)	LIGHT YELLOW
PH VALUE	6.0
REFRACTIVE INDEX (@ 27 DEG)	1.550

For further information, please contact:
 "SHHIVTEK INDUSTRIES PRIVATE LIMITED"
 1419, Tower-1, DLF Corporate Green, Sector-74 A SPR Road,
 Gurugram, Haryana-122004 (INDIA)
 Phone no: 0124-6904448

www.shiva-group.com

Information in this publication is believed to be accurate and is given in good faith, but it is for the customer to satisfy itself of the suitability for its own particular purpose. Accordingly, Shiva Group gives no warranty as to the fitness of the product for any particular purpose and any implied warranty or condition (statutory or otherwise) is excluded except to the extent that such exclusion is prevented by law. Freedom under Patent, Copyright and Designs cannot be assumed.

Disclaimer:-

Color indicated are with Optical Brightener (OB+) only. Without OB+ color increases by 40-50 Hu.

Viscosity measured is on specific batch made from specific paraffin range. The viscosity can change from $\pm$ 5-7 poise depending upon incoming raw material range.

TDS prepared is on specific batch of specific paraffin range only. Some minor range bound differences may appear form batch to batch due to change in paraffin range.

Samples kept for 12 hours at a specified temperature before conducting test.

The specifications are solely checked by SHIVA in house Laboratory and are indicative. All specs needs to be cross examined before confirming commercial deals.

This document cannot be used for any legal purpose.

Revised Date: 05- Feb-25

Shivtek Spechemi Industries Ltd

(Formerly known as Shhivtek Industries Private Limited)

CIN No. U24100DL2009PLC188730

1419, DLF Corporate Green Tower 1, Sector 74 A, Southern Peripheral Road (SPR),
 Gurugram, Haryana-122004 (India).

+91-124-6904448 • info@shivtekspechemi.com, sales@shivtekspechemi.com

• www.shivtekspechemi.com, www.shiva-group.com



SHIVACHLOR – 2442

SHIVACHLOR – 2442 is a chlorinated paraffin based on a (C10-C13) paraffin and is ROHS compliant.

It is a versatile and low colour grade used in a number of industries and applications ranging from use as a secondary plasticiser and flame retardant additive in PVC to use in paints, sealants and adhesives.

Further information may be obtained from the website 'www.shiva-group.com/www.shivtekspechemi.com'.

'SHIVACHLOR – 2442' is not classified as hazardous for transport or use and is available in HmHDPE/STEEL drums of 220-275 kgs nett weight as well as in IBC (1200 kg- 1300 kg) or in flexi Bags/Bulk Isotainers

TECHNICAL DATA SHEET OF SHIVACHLOR – 2442 CP PLASTICISER

SP.GVT @ 27 DEGREES CELCIUS	1400
COLOUR HAZEN (Hu)	25-35
CHLORINE CONTENT (%W/W)	62-63%
VISCOSITY (27 DEG) POISE (BROOKFIELD)	15-25
FREE MINERAL ACIDITY	0.00010
FREE CHLORINE	NIL
VOLATILE LOSS (130 DEG/3 HRS) %	0.35 MAX
HEAT STABILITY (180 DEG/30 MIN)	LIGHT YELLOW
PH VALUE	6.5
REFRACTIVE INDEX (@ 27 DEG)	1.540

For further information, please contact:

"SHIVTEK SPECHEMI INDUSTRIES LTD"

1419, Tower-1, DLF Corporate Green, Sector-74 A SPR Road,

Gurugram, Haryana-122004 (INDIA)

Phone no: 0124-6904448

www.shiva-group.com

Information in this publication is believed to be accurate and is given in good faith, but it is for the customer to satisfy itself of the suitability for its own particular purpose. Accordingly, Shiva Group gives no warranty as to the fitness of the product for any particular purpose and any implied warranty or condition (statutory or otherwise) is excluded except to the extent that such exclusion is prevented by law. Freedom under Patent, Copyright and Designs cannot be assumed.

Disclaimer:-

Color indicated are with Optical Brightener (OB+) only. Without OB+ color increases by 40-50 Hu.

Viscosity measured is on specific batch made from specific paraffin range. The viscosity can change from $\pm 5-7$ poise depending upon incoming raw material range.

TDS prepared is on specific batch of specific paraffin range only. Some minor range bound differences may appear from batch to batch due to change in paraffin range.

Samples kept for 12 hours at a specified temperature before conducting test.

The specifications are solely checked by SHIVA in house Laboratory and are indicative. All specs needs to be cross examined before confirming commercial deals.

This document cannot be used for any legal purpose.

Revised Date: 05- Feb-25

Shivtek Spechemi Industries Ltd

(Formerly known as Shvivek Industries Private Limited)

CIN No. U24100DL2009PLC188730

1419, DLF Corporate Green Tower 1, Sector 74 A, Southern Peripheral Road (SPR), Gurugram, Haryana-122004 (India).

+91-124-6904448 info@shivtekspechemi.com, sales@shivtekspechemi.com

www.shivtekspechemi.com, www.shiva-group.com



SHIVACHLOR OPT SUPER – 242 (SP)

SHIVACHLOR OPT SUPER – 242 (SP) is a chlorinated paraffin based on a (C10-C13) paraffin and is REACH and ROHS compliant. It is a versatile and low colour grade used in a number of industries and applications ranging from use as a Secondary plasticizer and flame retardant additive in PVC to use in paints, sealants and adhesives.

Further information may be obtained from the website 'www.shiva-group.com/www.shivtekspechemi.com'.

SHIVACHLOR OPT SUPER – 242 (SP) is not classified as hazardous for transport or use and is available in HMHDPE/STEEL drums of 220-275 kgs nett weight as well as in IBC (1200 kg- 1300 kg) or in flexi Bags/Bulk Isotaines.

TECHNICAL DATA SHEET OF SHIVACHLOR OPT SUPER – 242 (SP) CP PLASTICISER

SP.GVT @ 27 DEGREES CELCIUS	1380-1410
COLOUR HAZEN (Hu)	20(+10)
CHLORINE CONTENT (%W/W)	62 max
VISCOSITY (27 DEG) POISE (BROOKFIELD)	25(+20)
FREE MINERAL ACIDITY	0.00010
FREE CHLORINE	NIL
VOLATILE LOSS (130 DEG/3 HRS) %	N/A
HEAT STABILITY (180 DEG/30 MIN)	MINOR COLOUR CHANGE
PH VALUE	6.5
REFRACTIVE INDEX (@ 27 DEG)	>1.5

For further information, please contact:

"SHIVTEK SPECHEMI INDUSTRIES LTD"

1419, Tower-1, DLF Corporate Green, Sector-74 A SPR Road,
Gurugram, Haryana-122004 (INDIA)

Phone no: 0124-6904448

www.shiva-group.com

Information in this publication is believed to be accurate and is given in good faith, but it is for the customer to satisfy itself of the suitability for its own particular purpose. Accordingly, Shiva Group gives no warranty as to the fitness of the product for any particular purpose and any implied warranty or condition (statutory or otherwise) is excluded except to the extent that such exclusion is prevented by law. Freedom under Patent, Copyright and Designs cannot be assumed.

Disclaimer:-

Color indicated are with Optical Brightener (OB+) only. Without OB+ color increases by 40-50 Hu.

Viscosity measured is on specific batch made from specific paraffin range. The viscosity can change from $\pm$ 5-7 poise depending upon incoming raw material range.

TDS prepared is on specific batch of specific paraffin range only. Some minor range bound differences may appear from batch to batch due to change in paraffin range.

Samples kept for 12 hours at a specified temperature before conducting test.

The specifications are solely checked by SHIVA in house Laboratory and are indicative. All specs needs to be cross examined before confirming commercial deals.

This document cannot be used for any legal purpose.

Revised Date: 05- Feb-25

Shivtek Spechemi Industries Ltd

(Formerly known as Shihivtek Industries Private Limited)

CIN No. U24100DL2009PLC188730

1419, DLF Corporate Green Tower 1, Sector 74 A, Southern Peripheral Road (SPR),
Gurugram, Haryana-122004 (India).

+91-124-6904448 info@shivtekspechemi.com, sales@shivtekspechemi.com

www.shivtekspechemi.com, www.shiva-group.com



SHIVACHLOR – 1900

SHIVACHLOR – 1900 is a chlorinated paraffin based on a (C10-C13) paraffin and is ROHS compliant. It is a versatile and low colour grade used in a number of industries and applications ranging from use as a secondary plasticiser and flame retardant additive in PVC to use in paints, sealants and adhesives.

Further information may be obtained from the website 'www.shiva-group.com/www.shivtekspechemi.com'.

SHIVACHLOR – 1900 is not classified as hazardous for transport or use and is available in HMHDPE/STEEL drums of 220-275 kgs nett weight as well as in IBC (1200 kg- 1300 kg) or in flexi Bags/Bulk Isotaines.

TECHNICAL DATA SHEET OF SHIVACHLOR – 1900 CP PLASTICISER

SP.GVT @ 27 DEGREES CELCIUS	1440-1460
COLOUR HAZEN (Hu)	40-70
CHLORINE CONTENT (%W/W)	64-67%
VISCOSITY (27 DEG) POISE (BROOKFIELD)	200-350
FREE MINERAL ACIDITY	N.A
FREE CHLORINE	NIL
VOLATILE LOSS (130 DEG/3 HRS) %	N.A
HEAT STABILITY (180 DEG/30 MIN)	DEEP YELLOW
PH VALUE	6.0
REFRACTIVE INDEX (@ 27 DEG)	1.500 MAX

For further information, please contact:

"SHIVTEK SPECHEMI INDUSTRIES LTD"

1419, Tower-1, DLF Corporate Green, Sector-74 A SPR Road,

Gurugram, Haryana-122004 (INDIA)

Phone no: 0124-6904448

www.shiva-group.com

Information in this publication is believed to be accurate and is given in good faith, but it is for the customer to satisfy itself of the suitability for its own particular purpose. Accordingly, Shiva Group gives no warranty as to the fitness of the product for any particular purpose and any implied warranty or condition (statutory or otherwise) is excluded except to the extent that such exclusion is prevented by law. Freedom under Patent, Copyright and Designs cannot be assumed.

Disclaimer:-

Color indicated are with Optical Brightener (OB+) only. Without OB+ color increases by 40-50 Hu.

Viscosity measured is on specific batch made from specific paraffin range. The viscosity can change from $\pm$ 5-7 poise depending upon incoming raw material range.

TDS prepared is on specific batch of specific paraffin range only. Some minor range bound differences may appear from batch to batch due to change in paraffin range.

Samples kept for 12 hours at a specified temperature before conducting test.

The specifications are solely checked by SHIVA in house Laboratory and are indicative. All specs needs to be cross examined before confirming commercial deals.

This document cannot be used for any legal purpose.

Revised Date: 05- Feb-25

Shivtek Spechemi Industries Ltd

(Formerly known as Shshivtek Industries Private Limited)

CIN No. U24100DL2009PLC188730

1419, DLF Corporate Green Tower 1, Sector 74 A, Southern Peripheral Road (SPR), Gurugram, Haryana-122004 (India).

+91-124-6904448 info@shivtekspechemi.com, sales@shivtekspechemi.com

www.shivtekspechemi.com, www.shiva-group.com



SHIVACHLOR – 1950

SHIVACHLOR – 1950 is a chlorinated paraffin based on a (C10-C13) paraffin and is ROHS compliant. It is a versatile and low colour grade used in a number of industries and applications ranging from use as a secondary plasticiser and flame retardant additive in PVC to use in paints, sealants and adhesives.

Further information may be obtained from the website 'www.shiva-group.com/www.shivtekspechemi.com'.

SHIVACHLOR – 1950 is not classified as hazardous for transport or use and is available in HMHDPE/STEEL drums of 220-275 kgs nett weight as well as in IBC (1200 kg- 1300 kg) or in flexi Bags/Bulk Isotaines

TECHNICAL DATA SHEET OF SHIVACHLOR – 1950 CP PLASTICISER

SP.GVT @ 27 DEGREES CELCIUS	1500
COLOUR HAZEN (Hu)	60-80
CHLORINE CONTENT (%W/W)	69-70%
VISCOSITY (27 DEG) POISE (BROOKFIELD)	420
FREE MINERAL ACIDITY	0.00010
FREE CHLORINE	NIL
VOLATILE LOSS (130 DEG/3 HRS) %	0.2 MAX
HEAT STABILITY (180 DEG/30 MIN)	LIGHT YELLOW
PH VALUE	6.5
REFRACTIVE INDEX (@ 27 DEG)	1.515

For further information, please contact:

"SHIVTEK SPECHEMI INDUSTRIES LTD"

1419, Tower-1, DLF Corporate Green, Sector-74 A SPR Road,

Gurugram, Haryana-122004 (INDIA)

Phone no: 0124-6904448

www.shiva-group.com

Information in this publication is believed to be accurate and is given in good faith, but it is for the customer to satisfy itself of the suitability for its own particular purpose. Accordingly, Shiva Group gives no warranty as to the fitness of the product for any particular purpose and any implied warranty or condition (statutory or otherwise) is excluded except to the extent that such exclusion is prevented by law. Freedom under Patent, Copyright and Designs cannot be assumed.

Disclaimer:-

Color indicated are with Optical Brightener (OB+) only. Without OB+ color increases by 40-50 Hu.

Viscosity measured is on specific batch made from specific paraffin range. The viscosity can change from $\pm$ 5-7 poise depending upon incoming raw material range.

TDS prepared is on specific batch of specific paraffin range only. Some minor range bound differences may appear from batch to batch due to change in paraffin range.

Samples kept for 12 hours at a specified temperature before conducting test.

The specifications are solely checked by SHIVA in house Laboratory and are indicative. All specs needs to be cross examined before confirming commercial deals.

This document cannot be used for any legal purpose.

Revised Date: 05- Feb-25

Shivtek Spechemi Industries Ltd

(Formerly known as Shihvtek Industries Private Limited)

CIN No. U24100DL2009PLC188730

1419, DLF Corporate Green Tower 1, Sector 74 A, Southern Peripheral Road (SPR), Gurugram, Haryana-122004 (India).

+91-124-6904448 • info@shivtekspechemi.com, sales@shivtekspechemi.com

• www.shivtekspechemi.com, www.shiva-group.com



SHIVACHLOR – 1910

SHIVACHLOR – 1910 ' is a chlorinated paraffin based on a (C10-C13) paraffin and is ROHS compliant. It is a versatile and low colour grade used in a number of industries and applications ranging from use as a secondary plasticiser and flame retardant additive in PVC to use in paints, sealants and adhesives.

Further information may be obtained from the website 'www.shiva-group.com/www.shivtekspechemi.com'.

'SHIVACHLOR – 1910' is not classified as hazardous for transport or use and is available in HMHDPE/STEEL drums of 220-275 kgs nett weight as well as in IBC (1200 kg- 1300 kg) or in flexi Bags/Bulk Isotaines

TECHNICAL DATA SHEET OF SHIVACHLOR – 1910 CP PLASTICISER

SP.GVT @ 27 DEGREES CELCIUS	1470
COLOUR HAZEN (Hu)	100-150
CHLORINE CONTENT (%W/W)	68-70%
VISCOSITY (27 DEG) POISE (BROOKFIELD)	N.A.
FREE MINERAL ACIDITY	0.00010
FREE CHLORINE	NIL
VOLATILE LOSS (130 DEG/3 HRS) %	0.2 MAX
HEAT STABILITY (180 DEG/30 MIN)	LIGHT YELLOW
PH VALUE	6.5
REFRACTIVE INDEX (@ 27 DEG)	1.540

For further information, please contact:

"SHIVTEK SPECHEMI INDUSTRIES LTD"

1419, Tower-1, DLF Corporate Green, Sector-74 A SPR Road,

Gurugram, Haryana-122004 (INDIA)

Phone no: 0124-6904448

www.shiva-group.com

Information in this publication is believed to be accurate and is given in good faith, but it is for the customer to satisfy itself of the suitability for its own particular purpose. Accordingly, Shiva Group gives no warranty as to the fitness of the product for any particular purpose and any implied warranty or condition (statutory or otherwise) is excluded except to the extent that such exclusion is prevented by law. Freedom under Patent, Copyright and Designs cannot be assumed.

Disclaimer:-

Color indicated are with Optical Brightener (OB+) only. Without OB+ color increases by 40-50 Hu.

Viscosity measured is on specific batch made from specific paraffin range. The viscosity can change from $\pm 5-7$ poise depending upon incoming raw material range.

TDS prepared is on specific batch of specific paraffin range only. Some minor range bound differences may appear form batch to batch due to change in paraffin range.

Samples kept for 12 hours at a specified temperature before conducting test.

The specifications are solely checked by SHIVA in house Laboratory and are indicative. All specs needs to be cross examined before confirming commercial deals.

This document cannot be used for any legal purpose.

Revised Date: 05- Feb-25

Shivtek Spechemi Industries Ltd

(Formerly known as Shhivtek Industries Private Limited)

CIN No. U24100DL2009PLC188730

1419, DLF Corporate Green Tower 1, Sector 74 A, Southern Peripheral Road (SPR), Gurugram, Haryana-122004 (India).

+91-124-6904448 • info@shivtekspechemi.com, sales@shivtekspechemi.com

• www.shivtekspechemi.com, www.shiva-group.com

