



RE-DEFINING HORIZONS
www.shiva-group.com



GOVT. RECOGNISED
STAR EXPORT HOUSE



ISO 14001:2015
AND ISO 9001:2015
CERTIFIED FACILITIES

GRADE KG SERIES

KG GRADE is a Chlorinated Paraffin based on a refined short chain length C9-C20 paraffin. It is a versatile and low colour grade used in a number of industries and applications ranging from use as a secondary plasticizer and flame retardant additive in PVC to use in paints, sealants and adhesives.

Further information may be obtained from the website 'www.shiva-group.com'.

'KG GRADE' is not classified as hazardous for transport or use and is available in HMHDPE/STEEL drums of 220 kgs nett weight as well as in IBC (1200kg-1300kg) or in Flexi Bags/Bulk Isotainers.

TECHNICAL DATA SHEET											
GRADE	Kg30	Kg40	Kg50	Kg52	Kg55	Kg58	Kg60	Kg62	Kg65	Kg68	Kg70
SPECIFIC GRAVITY	1100	1200	1300	1320	1350	1380	1400	1420	1450	1480	1500
COLOUR HAZEN (Hu)	65 Max	65 Max	70 Max	70 Max	70 Max	80 Max	80 Max	80 Max	90 Max	100 Max	100 Max
CHLORINE CONTENT (%W/W)	45-42	44-46	53-54	54-55	56-58	59-60	60-62	62-64	64-66	66.68	69-70
VISCOSITY (30 DEG) POISE (BROOKFIELD)	<1	<5	10(+5)	25 Max	40 Max	60 Max	80 Max	120 Max	280 Max	375 Max	550 Max
FREE MINERAL ACIDITY	0.0001	0.0001	0.0001	0.0001	0.0001	0.0001	0.0001	0.0001	0.0001	0.0001	0.00001
FREE CHLORINE	NIL	NIL	NIL	NIL	NIL	NIL	NIL	NIL	NIL	NIL	NIL
VOLATILE LOSS (130 DEG/3 HRS) %	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A
HEAT STABILITY (180 DEG/ 15 MIN)	Y(G.Y)	Y(G.Y)	Y(G.Y)	Y(G.Y)	Y(G.Y)	Y(G.Y)	Y(G.Y)	Y(G.Y)	Y(G.Y)	Y(G.Y)	Y(G.Y)
PH VALUE	6.0	6.0	6.0	6.0	6.0	6.0	6.0	6.0	6.0	6.0	6.0
REFRACTIVE INDEX (@ 27 DEG)	1.50	1.51	1.52	1.53	1.54	1.56	1.57	1.51	1.51	1.54	1.54

*L.Y = Light Yellow and G.Y= Golden Yellow

For further information, please contact:

"Shiva House"

802-805, 8th Floor, Pearls Best Height Tower – II

Netaji Subhash Place, Pitampura, New Delhi – 110034, INDIA.

Ph.: 011-43544444 (100 Lines)

www.shiva-group.com

Information in this publication is believed to be accurate and is given in good faith, but it is for the customer to satisfy itself of the suitability for its own particular purpose. Accordingly, Shiva Group gives no warranty as to the fitness of the product for any particular purpose and any implied warranty or condition (statutory or otherwise) is excluded except to the extent that such exclusion is prevented by law. Freedom under Patent, Copyright and Designs cannot be assumed.

Disclaimer:-

Color indicated are with Optical Brightener (OB+) only. Without OB+ color increases by 40-50 Hu.

Viscosity measured is on specific batch made from specific paraffin range. The viscosity can change from $\pm 5-7$ poise depending upon incoming raw material range.

TDS prepared is on specific batch of specific paraffin range only. Some minor range bound differences may appear from batch to batch due to change in paraffin range.

Samples kept for 12 hours at a specified temperature before conducting test.

The specifications are solely checked by SHIVA in house Laboratory and are indicative. All specs needs to be cross examined before confirming commercial deals.

This document cannot be used for any legal purpose.



SCAN ME

SHIVACHLOR – KG-30(LV)

SHIVACHLOR – KG-30(LV) is Chlorinated Paraffin based on a Mixed Paraffin and is RoHS compliant. It is a versatile and low colour grade used in a number of industries and applications ranging from use as a Secondary plasticizer and flame retardant additive in PVC to use in paints, sealants and adhesives.

Further information may be obtained from the website 'www.shiva-group.com'.

'**SHIVACHLOR – KG-30(LV)** is not classified as hazardous for transport or use and is available in HMHDPE/STEEL drums of 220 kgs nett weight as well as in IBC (1200kg-1300kg) or in Flexi Bags/Bulk Isotainers.

TECHNICAL DATA SHEET OF KG-30(LV) CP PLASTICISER	
SP.GVT @ 27DEGREESCELCIUS	1100-1130
COLOUR HAZEN(Hu)	60-120
CHLORINE CONTENT(%W/W)	40-43%
VISCOSITY(27DEG)POISE(BROOKFIELD)	<1.0 POISE
FREE CHLORINE MAX.	NIL
HEAT STABILITY(180 DEG/30 MIN)	LIGHT YELLOW BROWN
PH VALUE MIN.	6.0
REFRACTIVE INDEX(@ 27DEG)	1.50 MAX

For further information, please contact:

"Shiva House"

802-805, 8th Floor, Pearls Best Height Tower – II
Netaji Subhash Place, Pitampura, New Delhi – 110034, INDIA.
Ph.: 011-43544444 (100 Lines)
www.shiva-group.com

Information in this publication is believed to be accurate and is given in good faith, but it is for the customer to satisfy itself of the suitability for its own particular purpose. Accordingly, Shiva Group gives no warranty as to the fitness of the product for any particular purpose and any implied warranty or condition (statutory or otherwise) is excluded except to the extent that such exclusion is prevented by law. Freedom under Patent, Copyright and Designs cannot be assumed.

Disclaimer:-

Color indicated are with Optical Brightener (OB+) only. Without OB+ color increases by 40-50 Hu.

Viscosity measured is on specific batch made from specific paraffin range. The viscosity can change from $\pm 5-7$ poise depending upon incoming raw material range. TDS prepared is on specific batch of specific paraffin range only. Some minor range bound differences may appear from batch to batch due to change in paraffin range.

Samples kept for 12 hours at a specified temperature before conducting test.

The specifications are solely checked by SHIVA in house Laboratory and are indicative. All specs needs to be cross examined before confirming commercial deals.

This document cannot be used for any legal purpose.



SHIVACHLOR – KG-40(LV)

SHIVACHLOR – KG-40(LV) is Chlorinated Paraffin based on a Mixed Paraffin and is RoHS compliant.

It is a versatile and low colour grade used in a number of industries and applications ranging from use as a Secondary plasticizer and flame retardant additive in PVC to use in paints, sealants and adhesives.

Further information may be obtained from the website 'www.shiva-group.com'.

'**SHIVACHLOR – KG-40(LV)** is not classified as hazardous for transport or use and is available in HMHDPE/STEEL drums of 220 kgs nett weight as well as in IBC (1200kg-1300kg) or in Flexi Bags/Bulk Isotaines.

TECHNICAL DATA SHEET OF KG-40(LV) CP PLASTICISER	
SP.GVT @ 27DEGREESCELCIUS	1200 -1220
COLOUR HAZEN(Hu)	60-120
CHLORINE CONTENT(%W/W)	44-46%
VISCOSITY(27DEG)POISE(BROOKFIELD)	1-3 Poise
FREE CHLORINE MAX.	NIL
HEAT STABILITY(180 DEG/30 MIN)	LIGHT YELLOW BROWN
PH VALUE MIN.	6.0
REFRACTIVE INDEX(@ 27DEG)MAX	1.55 MAX

For further information, please contact:

"Shiva House"

802-805, 8th Floor, Pearls Best Height Tower – II

Netaji Subhash Place, Pitampura, New Delhi – 110034, INDIA.

Ph.: 011-43544444 (100 Lines)

www.shiva-group.com

Information in this publication is believed to be accurate and is given in good faith, but it is for the customer to satisfy itself of the suitability for its own particular purpose. Accordingly, Shiva Group gives no warranty as to the fitness of the product for any particular purpose and any implied warranty or condition (statutory or otherwise) is excluded except to the extent that such exclusion is prevented by law. Freedom under Patent, Copyright and Designs cannot be assumed.

Disclaimer:-

Color indicated are with Optical Brightener (OB+) only. Without OB+ color increases by 40-50 Hu.

Viscosity measured is on specific batch made from specific paraffin range. The viscosity can change from $\pm 5-7$ poise depending upon incoming raw material range.

TDS prepared is on specific batch of specific paraffin range only. Some minor range bound differences may appear from batch to batch due to change in paraffin range.

Samples kept for 12 hours at a specified temperature before conducting test.

The specifications are solely checked by SHIVA in house Laboratory and are indicative. All specs needs to be cross examined before confirming commercial deals.

This document cannot be used for any legal purpose.



SHIVACHLOR – KG-45(LV)

SHIVACHLOR – KG-45(LV) is Chlorinated Paraffin based on a Mixed Paraffin and is RoHS compliant.

It is a versatile and low colour grade used in a number of industries and applications ranging from use as a Secondary plasticizer and flame retardant additive in PVC to use in paints, sealants and adhesives.

Further information may be obtained from the website 'www.shiva-group.com'.

'**SHIVACHLOR – KG-45(LV)** is not classified as hazardous for transport or use and is available in HMHDPE/STEEL drums of 220 kgs nett weight as well as in IBC (1200kg-1300kg) or in Flexi Bags/Bulk Isotaines.

TECHNICAL DATA SHEET OF KG-45(LV) CP PLASTICISER	
SP.GVT @ 27DEGREESCELCIUS	1.240-1.250
COLOUR HAZEN(Hu)	80
CHLORINE CONTENT(%W/W)	46-47%
VISCOSITY(27DEG)POISE(BROOKFIELD)	<5
FREE MINERAL ACIDITY MIN.	0.00010
FREE CHLORINE MAX.	NIL
VOLATILE LOSS(130 DEG/3 HRS) %	N/A
HEAT STABILITY(180 DEG/30 MIN)	LIGHT YELLOW
PH VALUE MIN.	6.0
REFRACTIVE INDEX(@ 27DEG)	1.55

For further information, please contact:

"Shiva House"

802-805, 8th Floor, Pearls Best Height Tower – II

Netaji Subhash Place, Pitampura, New Delhi – 110034, INDIA.

Ph.: 011-43544444 (100 Lines)

www.shiva-group.com

Information in this publication is believed to be accurate and is given in good faith, but it is for the customer to satisfy itself of the suitability for its own particular purpose. Accordingly, Shiva Group gives no warranty as to the fitness of the product for any particular purpose and any implied warranty or condition (statutory or otherwise) is excluded except to the extent that such exclusion is prevented by law. Freedom under Patent, Copyright and Designs cannot be assumed.

Disclaimer:-

Color indicated are with Optical Brightener (OB+) only. Without OB+ color increases by 40-50 Hu.

Viscosity measured is on specific batch made from specific paraffin range. The viscosity can change from $\pm 5-7$ poise depending upon incoming raw material range.

TDS prepared is on specific batch of specific paraffin range only. Some minor range bound differences may appear from batch to batch due to change in paraffin range.

Samples kept for 12 hours at a specified temperature before conducting test.

The specifications are solely checked by SHIVA in house Laboratory and are indicative. All specs needs to be cross examined before confirming commercial deals.

This document cannot be used for any legal purpose.



SHIVACHLOR – KG-48(LV)

SHIVACHLOR – KG-48(LV) is a Chlorinated Paraffin liquid based on a mixed paraffin and is REACH And RoHS compliant.

It is a versatile and low colour grade used in a number of industries and applications Ranging from use a secondary plasticizer and flame retardant additive in PVC to use in paints, sealants And adhesives.

Further information may be obtained from the website 'www.shiva-group.com'.

'SHIVACHLOR – KG-48(LV)' is not classified as hazardous for transport or use and is available HMHDPE/STEEL drums of 220 kgs nett weight as well as in IBC (1200kg-1300kg) or in Flexi Bags/Bulk Isotaines.

TECHNICAL DATA SHEET OF SHIVACHLOR – KG-48(LV)	
SP.GVT @ 27DEGREESCELCIUS	1260-1290
COLOUR HAZEN(Hu)	60-140
CHLORINE CONTENT(%W/W)	51-52%
VISCOSITY(27DEG)POISE(BROOKFIELD)	3-6 Poise
FREE CHLORINE MAX.	NIL
HEAT STABILITY(180 DEG/30 MIN)	LIGHT YELLOW BROWN
PH VALUE MIN.	6.0
REFRACTIVE INDEX(@ 27DEG)MAX	1.55 Max

For further information, please contact:

"Shiva House"

802-805, 8th Floor, Pearls Best Height Tower – II
Netaji Subhash Place, Pitampura, New Delhi – 110034, INDIA.
Ph.: 011-43544444 (100 Lines)
www.shiva-group.com

Information in this publication is believed to be accurate and is given in good faith, but it is for the customer to satisfy itself of the suitability for its own particular purpose. Accordingly, Shiva Group gives no warranty as to the fitness of the product for any particular purpose and any implied warranty or condition (statutory or otherwise) is excluded except to the extent that such exclusion is prevented by law. Freedom under Patent, Copyright and Designs cannot be assumed.

Disclaimer:-

Color indicated are with Optical Brightener (OB+) only. Without OB+ color increases by 40-50 Hu.

Viscosity measured is on specific batch made from specific paraffin range. The viscosity can change from $\pm 5-7$ poise depending upon incoming raw material range. TDS prepared is on specific batch of specific paraffin range only. Some minor range bound differences may appear form batch to batch due to change in paraffin range.

Samples kept for 12 hours at a specified temperature before conducting test.

The specifications are solely checked by SHIVA in house Laboratory and are indicative. All specs needs to be cross examined before confirming commercial deals.

This document cannot be used for any legal purpose.



SHIVACHLOR – KG-50(LV)

SHIVACHLOR – KG-50(LV) is Chlorinated Paraffin based on a Mixed Paraffin and is RoHS compliant.

It is a versatile and low colour grade used in a number of industries and applications ranging from use as a Secondary plasticizer and flame retardant additive in PVC to use in paints, sealants and adhesives.

Further information may be obtained from the website 'www.shiva-group.com'.

'**SHIVACHLOR – KG-50(LV)** is not classified as hazardous for transport or use and is available in HMHDPE/STEEL drums of 220 kgs nett weight as well as in IBC (1200kg-1300kg) or in Flexi Bags/Bulk Isotaines.

TECHNICAL DATA SHEET OF KG-50(LV) CP PLASTICISER	
SP.GVT @ 27DEGREESCELCIUS	1350-1360
COLOUR HAZEN(Hu)	35-50
CHLORINE CONTENT(%W/W)	57-58%
VISCOSITY(27DEG)POISE(BROOKFIELD)	5-12
FREE MINERAL ACIDITY MIN.	0.00010
FREE CHLORINE MAX.	NIL
VOLATILE LOSS(130 DEG/3 HRS) %	0.3 MAX
HEAT STABILITY(180 DEG/30 MIN)	LIGHT YELLOW
PH VALUE MIN.	6.0
REFRACTIVE INDEX(@ 27DEG)	1.550

For further information, please contact:

"Shiva House"

802-805, 8th Floor, Pearls Best Height Tower – II

Netaji Subhash Place, Pitampura, New Delhi – 110034, INDIA.

Ph.: 011-43544444 (100 Lines)

www.shiva-group.com

Information in this publication is believed to be accurate and is given in good faith, but it is for the customer to satisfy itself of the suitability for its own particular purpose. Accordingly, Shiva Group gives no warranty as to the fitness of the product for any particular purpose and any implied warranty or condition (statutory or otherwise) is excluded except to the extent that such exclusion is prevented by law. Freedom under Patent, Copyright and Designs cannot be assumed.

Disclaimer:-

Color indicated are with Optical Brightener (OB+) only. Without OB+ color increases by 40-50 Hu.

Viscosity measured is on specific batch made from specific paraffin range. The viscosity can change from $\pm 5-7$ poise depending upon incoming raw material range.

TDS prepared is on specific batch of specific paraffin range only. Some minor range bound differences may appear from batch to batch due to change in paraffin range.

Samples kept for 12 hours at a specified temperature before conducting test.

The specifications are solely checked by SHIVA in house Laboratory and are indicative. All specs needs to be cross examined before confirming commercial deals.

This document cannot be used for any legal purpose.

