

SHIVACHLOR – 0440 LV

SHIVACHLOR - 0440 LV Grade is a chlorinated Paraffin based on refined short chain length (C10-C22) Paraffin.

It is a versatile and low colour grade used in a number of industries and applications ranging from use as a secondary plasticizer and flame retardant additive in PVC to use in paints, sealants and adhesives.

Further information may be obtained from the website 'www.shivtekspechemi.com'.

'SHIVACHLOR –0440LV' is not classified as hazardous for transport or use and is available in HMHDPE/STEEL drums of 220-275 Kgs net weight as well as in IBC (1200 kg- 1300 kg) or in flexi Bags/Bulk isotainers.

TECHNICAL DATA SHEET OF SHIVACHLOR – 0440 LV CP PLASTICISER

SP.GVT @ 27 DEGREES CELCIUS	1300
COLOUR HAZEN (Hu)	100 MAX
CHLORINE CONTENT (%W/W)	53-54 %
VISCOSITY (27 DEG) POISE (BROOKFIELD)	80
FREE MINERAL ACIDITY	0.0001
FREE CHLORINE	NIL
VOLATILE LOSS (130 DEG/3 HRS) %	NA
HEAT STABILITY (180 DEG/20 MIN)	DEEP YELLOW
PH VALUE MIN	6.0
REFRACTIVE INDEX (@ 27 DEG) MIN	1.54

For further information, please contact:

"SHIVTEK SPECHEMI INDUSTRIES LTD"

24, 4th Floor, M3M Corner Walk, Golf Course Road(Extn), Sector-74,
Gurugram, Haryana-122004 (INDIA)

Phone no: +91-124-6584406

www.shivtekspechemi.com

Information in this publication is believed to be accurate and is given in good faith, but it is for the customer to satisfy itself of the suitability for its own particular purpose. Accordingly, Shiva Group gives no warranty as to the fitness of the product for any particular purpose and any implied warranty or condition (statutory or otherwise) is excluded except to the extent that such exclusion is prevented by law.

Freedom under Patent, Copyright and Designs cannot be assumed.

Disclaimer:-

Viscosity measured is on specific batch made from specific paraffin range. The viscosity can change from $\pm$ 5-7 Poise Depending upon incoming raw material range.

TDS prepared is on specific batch of specific paraffin range only. Some minor range bound differences may appear from batch to batch due to change in paraffin range.

Samples kept for 12 hours at a specified temperature before conducting test.

The specifications are solely checked by SHIVA in house Laboratory and are indicative. All specs need to be cross examined before confirming commercial deals.

This document cannot be used for any legal purpose.

Revised Date: 06- Aug -25

Shivtek Spechemi Industries Ltd

(Formerly known as Shhivtek Industries Private Limited)

CIN No. U24100DL2009PLC188730

● **Corp Office:** 24, 4th Floor, M3M Corner Walk, Golf Course Road(Extn), SPR, Sector-74,
Gurugram, Haryana-122004(India) Phone: +91-124-6584406

● **Regd Office:** Khasra No. 169, Ground Floor, Back Side, Alipur, Delhi- 110036

● info@shivtekspechemi.com, sales@shivtekspechemi.com ● www.shivtekspechemi.com

